CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 25/07/2020

Lab ID	:	**CP-2020-12-18-51**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	20-07-20
Customer ID	:	PCC
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M15 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	25/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	18/07/2020	25/07/2020	149.35 X 149.20 X 149.39	22283	8.042	268.6	12.1	12.3
2	PCC	M15	18/07/2020	25/07/2020	151.73 X 149.59 X 150.49	22697	8.989	281.5	12.4	
3	PCC	M15	18/07/2020	25/07/2020	150.04 X 149.65 X 149.96	22453	8.679	280.6	12.5	

• The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

••••End of Report••••

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-18-51** **Date: 15/08/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 20-07-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS code : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 15/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
1	PCC	M15	18/07/2020	15/08/2020	150.62 X 150.15 X 149.63	22616	8.774	397.6	17.6	17.6
2	PCC	M15	18/07/2020	15/08/2020	151.29 X 150.26 X 150.66	22733	8.378	409.2	18.0	
3	PCC	M15	18/07/2020	15/08/2020	151.46 X 151.69 X 150.68	22974	8.342	398.7	17.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig..... Date.....

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TP/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2020-12-18-51 **Date: 18/07/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 13-07-20

Customer ID : Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Footing Concrete	M25	11/07/2020	18/07/2020	149.46 X 151.25 X 149.38	22606	8.410	525.3	23.2	22.8
2	Footing Concrete	M25	11/07/2020	18/07/2020	150.95 X 150.36 X 150.78	22697	8.989	502.4	22.1	
3	Footing Concrete	M25	11/07/2020	18/07/2020	151.36 X 150.50 X 151.16	22780	8.089	523.8	23.0	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-18-51**

Date: 08/08/2020

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 13-07-20

Customer ID : Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Footing Concrete	M25	11/07/2020	08/08/2020	149.18 X 150.90 X 151.54	22510	8.446	613.9	27.3	27.5
2	Footing Concrete	M25	11/07/2020	08/08/2020	151.83 X 150.81 X 151.99	22898	8.858	610.0	26.6	
3	Footing Concrete	M25	11/07/2020	08/08/2020	149.72 X 150.79 X 150.43	22577	8.637	644.2	28.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-18-51** **Date: 18/07/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 13-07-20

Customer ID : Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 18/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Footing Concrete	M25	11/07/2020	18/07/2020	151.51 X 151.28 X 150.92	22921	8.410	546.0	23.8	23.0
2	Footing Concrete	M25	11/07/2020	18/07/2020	151.86 X 151.53 X 149.26	23012	8.989	519.7	22.6	
3	Footing Concrete	M25	11/07/2020	18/07/2020	151.77 X 151.28 X 151.20	22959	8.089	516.1	22.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig..... Date.....

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-55

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-18-51** **Date: 08/08/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 13-07-20

Customer ID : Footing Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 08/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Footing Concrete	M25	11/07/2020	08/08/2020	150.75 X 151.48 X 149.12	22836	8.446	621.5	27.2	27.5
2	Footing Concrete	M25	11/07/2020	08/08/2020	149.37 X 149.93 X 151.88	22395	8.858	602.3	26.9	
3	Footing Concrete	M25	11/07/2020	08/08/2020	151.59 X 151.40 X 150.24	22950	8.637	648.1	28.2	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.c
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

Scanned by TapScanner

Format No: CP/TF

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 23/07/2020

Lab ID	:	CP-2020-12-18-51
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyannapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-07-20
Customer ID	:	Plinth Beam Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS code	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete CL5
Date of test	:	23/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Plinth Beam Concrete	M25	16/07/2020	23/07/2020	151.40 X 151.16 X 149.96	22886	8.410	534.8	23.4	22.9
2	Plinth Beam Concrete	M25	16/07/2020	23/07/2020	149.21 X 151.55 X 149.29	22613	8.989	517.0	22.9	
3	Plinth Beam Concrete	M25	16/07/2020	23/07/2020	149.29 X 149.53 X 151.21	22324	8.089	503.1	22.5	

• The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CI

R KARTHIK R
Authorized
Quality

CIVIL Pro
BANGALORE

Page 1/1
****End of Report****

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 13/08/2020

Lab ID	:	**CP-2020-12-18-51**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	18-07-20
Customer ID	:	Plinth Beam Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	13/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Plinth Beam Concrete	M25	16/07/2020	13/08/2020	149.08 X 149.75 X 151.97	22325	8.446	610.4	27.3	27.7
2	Plinth Beam Concrete	M25	16/07/2020	13/08/2020	151.33 X 150.42 X 150.12	22764	8.858	612.4	26.9	
3	Plinth Beam Concrete	M25	16/07/2020	13/08/2020	149.43 X 149.39 X 151.73	22325	8.637	645.2	28.9	

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 27/07/2020

Lab ID	:	**CP-2020-12-18-51**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	22-07-20
Customer ID	:	GF Column Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	27/07/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Column Concrete	M25	20/07/2020	27/07/2020	149.33 X 149.71 X 149.18	22356	**8.410**	531.8	23.8	23.2
2	GF Column Concrete	M25	20/07/2020	27/07/2020	149.10 X 150.96 X 150.01	22507	**8.989**	510.9	22.7	
3	GF Column Concrete	M25	20/07/2020	27/07/2020	151.62 X 151.49 X 150.69	22970	**8.089**	527.5	23.0	

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro. BANGALORE Sig Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-18-51** **Date: 17/08/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 22-07-20

Customer ID : GF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 17/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Column Concrete	M25	20/07/2020	17/08/2020	149.37 X 150.19 X 151.22	22434	8.446	621.6	27.7	27.5
2	GF Column Concrete	M25	20/07/2020	17/08/2020	150.42 X 150.30 X 151.15	22608	8.858	598.3	26.5	
3	GF Column Concrete	M25	20/07/2020	17/08/2020	151.77 X 151.86 X 150.83	23048	8.637	655.3	28.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig. Date

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 17/08/2020

Lab ID	:	CP-2020-12-18-51
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	22-07-20
Customer ID	:	GF Column Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	17/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Column Concrete	M25	20/07/2020	17/08/2020	149.37 X 150.19 X 151.22	22434	8.446	621.6	27.7	27.5
2	GF Column Concrete	M25	20/07/2020	17/08/2020	150.42 X 150.30 X 151.15	22608	8.858	598.3	26.5	
3	GF Column Concrete	M25	20/07/2020	17/08/2020	151.77 X 151.86 X 150.83	23048	8.637	655.3	28.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig. Date

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 06/08/2020

Lab ID	:	**CP-2020-12-18-51**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	01-08-20
Customer ID	:	GF Lintel Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete CL5
Date of test	:	06/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Lintel Concrete	M25	30/07/2020	06/08/2020	151.11 X 150.97 X 150.17	22812	8.410	539.2	23.6	22.7
2	GF Lintel Concrete	M25	30/07/2020	06/08/2020	149.89 X 151.35 X 150.29	22686	8.989	500.1	22.0	
3	GF Lintel Concrete	M25	30/07/2020	06/08/2020	151.32 X 151.10 X 149.53	22863	8.089	511.8	22.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVI
R KARTHIK RE
Authorized S
Quality M

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gm

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |
[illegible] SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No : TC-5648

Format No: CP/TE/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2020-12-18-51** **Date: 06/08/2020**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Mandalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	01-08-20
Customer ID	:	GF Lintel Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	06/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Lintel Concrete	M25	30/07/2020	06/08/2020	151.11 X 150.97 X 150.17	22812	8.410	539.2	23.6	22.7
2	GF Lintel Concrete	M25	30/07/2020	06/08/2020	149.89 X 151.35 X 150.29	22686	8.989	500.1	22.0	
3	GF Lintel Concrete	M25	30/07/2020	06/08/2020	151.32 X 151.10 X 149.53	22863	8.089	511.8	22.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

MR KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No : TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 27/08/2020

Lab ID	:	CP-2020-12-18-51
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	01-08-20
Customer ID	:	GF Lintel Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	27/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Lintel Concrete	M25	30/07/2020	27/08/2020	151.59 X 150.81 X 149.51	22861	8.446	638.9	27.9	27.8
2	GF Lintel Concrete	M25	30/07/2020	27/08/2020	151.35 X 150.50 X 150.99	22779	8.858	608.6	26.7	
3	GF Lintel Concrete	M25	30/07/2020	27/08/2020	151.71 X 150.48 X 151.06	22829	8.637	656.1	28.7	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig. Date. BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 13/08/2020

Lab ID	:	**CP-2020-12-18-51**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-08-20
Customer ID	:	GF Staircase Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete CL5
Date of test	:	13/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Staircase Concrete	M25	06/08/2020	13/08/2020	150.64 X 151.98 X 150.31	22894	**8.410**	531.5	23.2	22.8
2	GF Staircase Concrete	M25	06/08/2020	13/08/2020	149.06 X 151.45 X 150.90	22574	**8.989**	505.2	22.4	
3	GF Staircase Concrete	M25	06/08/2020	13/08/2020	149.97 X 151.09 X 149.09	22659	**8.089**	520.0	22.9	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig. Date BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 03/09/2020

Lab ID	:	**CP-2020-12-18-51**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-08-20
Customer ID	:	GF Staircase Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	03/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	GF Staircase Concrete	M25	06/08/2020	03/09/2020	151.18 X 151.20 X 150.46	22858	8.446	631.5	27.6	27.4
2	GF Staircase Concrete	M25	06/08/2020	03/09/2020	150.84 X 150.61 X 150.85	22719	8.858	597.8	26.3	
3	GF Staircase Concrete	M25	06/08/2020	03/09/2020	150.72 X 150.53 X 150.63	22687	8.637	643.5	28.4	

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-18-51** **Date: 21/08/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-08-20

Customer ID : FF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 21/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Column Concrete	M25	14/08/2020	21/08/2020	151.82 X 151.63 X 150.47	23022	8.410	546.7	23.7	23.1
2	FF Column Concrete	M25	14/08/2020	21/08/2020	151.09 X 150.73 X 151.99	22774	8.989	523.8	23.0	
3	FF Column Concrete	M25	14/08/2020	21/08/2020	151.01 X 151.56 X 149.62	22887	8.089	519.4	22.7	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO BANGALORE Sig Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID	:	**CP-2020-12-18-51**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07
Agency	:	Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072
Customer's Reference	:	EE(Project)/Ynk Zone/WO/40/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-08-20
Customer ID	:	FF Column Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	11/09/2020

Date: 11/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^3)	Average Compressive Strength (N/mm^3)
1	FF Column Concrete	M25	14/08/2020	11/09/2020	149.07 X 151.13 X 150.65	22529	8.446	612.1	27.2	27.5
2	FF Column Concrete	M25	14/08/2020	11/09/2020	151.41 X 151.03 X 149.06	22868	8.858	610.9	26.7	
3	FF Column Concrete	M25	14/08/2020	11/09/2020	151.55 X 150.08 X 150.34	22744	8.637	652.0	28.7	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro BANGALORE Sig..... Date.....

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-12-18-51** **Date: 11/09/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-08-20

Customer ID : FF Column Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Column Concrete	M25	14/08/2020	11/09/2020	149.07 X 151.13 X 150.65	22529	8.446	612.1	27.2	27.5
2	FF Column Concrete	M25	14/08/2020	11/09/2020	151.41 X 151.03 X 149.06	22868	8.858	610.9	26.7	
3	FF Column Concrete	M25	14/08/2020	11/09/2020	151.55 X 150.08 X 150.34	22744	8.637	652.0	28.7	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig. Date

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned by TapScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

Lab ID : **CP-2020-12-18-51**

Date: 31/08/2020

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : Construction of Samudhaya Bhavana at Mariyanapalya in Ward No.07

Agency : Sri. Naveen S, #17, 4th Main Road, Kalyan Nagar, Moodalapalya, Bangalore-560072

Customer's Reference : EE(Project)/Ynk Zone/WO/40/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 26-08-20

Customer ID : FF Lintel Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	FF Lintel Concrete	M25	24/08/2020	31/08/2020	149.15 X 149.77 X 151.50	22338	8.410	535.1	24.0	23.0
2	FF Lintel Concrete	M25	24/08/2020	31/08/2020	149.46 X 150.85 X 150.22	22546	8.989	505.0	22.4	
3	FF Lintel Concrete	M25	24/08/2020	31/08/2020	151.63 X 150.25 X 149.52	22782	8.089	512.9	22.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

B KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES|

Scanned by TapScanner